

AGE DEFY

FIRST WRINKLES MOISTURIZING CREAM
FR24Q1.AGEDEFY



OVERVIEW

Age Defy helps you to defy the passage of time, thanks to a synergy of hyaluronic acids of different molecular weights and a hyaluronic acid-protecting active ingredient, to combat against the appearance of the first wrinkles. Its light texture provides long-lasting hydration and a “glowy” finish for a radiant complexion all day long.

Phase	Trade Name	Supplier	European I.N.C.I. Name	Function	%
A	Demineralized water	/	Aqua	/	47,20
	Aloe Vera BioPhytWater	GREENPHYT*	Aloe Barbadensis Leaf Water, Citric Acid, Sodium Benzoate, Potassium Sorbate	Hydrolate	19,00
	SymSave® H	SYMRISE*	Hydroxyacetophenone	Multifunctional conservation agent	0,50
	Hydrolite® 5 green	SYMRISE*	Pentylene Glycol		5,00
B	Propylene Glycol	/	Propylene Glycol	Humectant	3,00
	Sclerothix®	ALCHEMY*	Xanthan Gum, Sclerotium Gum, Algin	Gelling agent	1,00
	Sodium Hyaluronate Powder C MMW	HYUNDAI BIOLAND*	Sodium Hyaluronate	Active	0,50
C	Oligo-HA	HYUNDAI BIOLAND*	Hyaluronic Acid	Active	0,50
	Pellicer™ LB-30G	ASAHI KASEI*	Aqua, Sodium Dilauramidoglutamide Lysine, Butylene Glycol	Emulsifier	0,30
D	JD Jojoba Butter V	JOJOBA DESERT*	Simmondsia Chinensis Seed Oil, Stearyl Stearate, Rhus Verniciflua Peel Cera, Copernicia Cerifera Cera, Hydrogenated Vegetable Oil	Consistency agent	4,00
	Sumac Wax / Berry Wax	NOREVO*	Rhus Succedanea Fruit Cera / Rhus Verniciflua Peel Cera		2,00
	Elderberry Oil CA	SYMRISE*	Sambucus Nigra Seed Oil	Emollient	3,00
	Saboderm CVC MB	SABO*	Coco-Caprylate/Caprates		3,00
	Saboderm DOE MB	SABO*	Dicaprylyl Ether, Tocopherol		3,00
	Neossance™ Squalane	GIVAUDAN*	Squalane	Active emollient	5,00
	Decanox® MTS-50	ADM*	Tocopherol, Glycine Soja Oil	Anti-Oxidant	0,20
E	Sumicair Silken Matt Mica	SUDARSHAN*	Mica	Mattifying powder	1,50
	SynCrystal® Soft Ivory	ECKART*	Synthetic Fluorophlogopite, Titanium	Effect pigment	0,30
F	HyaluGuard	ICHIMARU PHARCOS*	Butylene Glycol, Aqua, Artemisia Capillaris Flower Extract	Active	1,00

* Please contact us to know in which country we are supplier of

PROCESS

PHASE A : Weigh and heat to 60 °C to dissolve SymSave® H.
 PHASE B : Mix and add to phase A.
 PHASE C : After gel creation, add to phase AB.
 PHASE D : Heat to 60 °C to melt waxes/butters, then add to phase ABC to emulsify at 2000rpm for 10-15min.
 PHASE E : Mix, then add when T=40 °C.
 PHASE F : Add when T=40 °C



PROPERTIES

APPEARANCE : beige-pink emulsion

VISCOSITY : 24240 cPs (Brookfield RVDV-I+, 5 rpm, 1 min, spindle 04).

pH : 4,13.

